

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)


(51) International Patent Classification ⁵ : D21H 21/16	A1	(11) International Publication Number: WO 94/13883
		(43) International Publication Date: 23 June 1994 (23.06.94)

(21) International Application Number: PCT/FI93/00481
(22) International Filing Date: 15 November 1993 (15.11.93)
(30) Priority Data:
925535 4 December 1992 (04.12.92) FI
(71) Applicant (for all designated States except US): RAISIO
CHEMICALS OY [FI/FI]; FIN-21200 Raisio (FI).
(72) Inventors; and
(75) Inventors/Applicants (for US only): ZETTER, Claes [FI/FI];
Sirkkälankatu 11 a, FIN-20500 Turku (FI). NURMINEN,
Markku [FI/FI]; Järviniityntie, FIN-21120 Raisio (FI).
(74) Agent: OY JALO ANT-WUORINEN AB; Iso Roobertinkatu
4-6 A, FIN-00120 Helsinki (FI).

(81) Designated States: AU, BR, CA, JP, KR, NZ, RU, US,
European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR,
IE, IT, LU, MC, NL, PT, SE).

Published
With international search report.

(54) Title: PROCESS FOR THE PREPARATION OF A HYDROPHOBIC SIZING AGENT DISPERSION



(57) Abstract

The present invention relates to a process for the preparation of hydrophobic sizing agent dispersions used in the paper and board industry. The invention is both a simple and an economical way of preparing a hydrophobic sizing agent dispersion either in the premises of a sizing agent supplier or a paper maker. The invention is based on a usage of a so-called high-pressure digester in the preparation of a hydrophobic sizing agent dispersion.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

Process for the preparation of a hydrophobic sizing agent dispersion

Hydrophobic sizing refers to the making of paper or board more or less water repellant. This property may be measured e.g. by the so-called Cobb test, in which the penetration of water into paper or board is measured as a function of time. The result is indicated as an absorption g/m^2 . In a properly hydrophobically sized product, the value is generally $< 25 \text{ g/m}^2$, whereas in a product, which has not been treated with sizing agents increasing the hydrophobicity, the value may be $> 100 \text{ g/m}^2$.

Conventional compounds used as a hydrophobic sizing agent include wood-based resin acids and their derivatives.

Nowadays, the paper and board industry has increasingly transferred to using for hydrophobic sizing so-called neutral sizing agents, which generally are compounds based on alkyl-ketene-dimer (AKD) or alkenyl-succinic-acid-anhydride (ASA).

Hydrophobic sizing agents are generally delivered to the paper and board mills as a water dispersion, in which the share of the active agent (AKD, ASA, resin) of the product is within the range of 5-50%. When a sizing agent of the ASA type is concerned, the sizing agent dispersion is primarily prepared at a paper or board mill.

Hydrophobic sizing agents are added to a pulp at the paper or board machine at the starting step of the manufacturing process. In certain cases, these sizing agents may be added also at a later step of the manufacturing process, e.g. at the size press. The quantities of the hydrophobic sizing agents to be used generally amount to 0.05-2.0% of the dry weight of the paper or board.

In addition to the active agent (AKD, ASA or wood resin),

a hydrophobic sizing agent dispersion contains stabilizers, surfactants and other additional chemicals. As a stabilizer e.g. cationic starch, cationic polyethylene imines, cationic polyacryl amides, gelatin or casein are used.

As surfactants e.g. sodium lignosulphonate or alkyl sulphonates are used.

Typical additional chemicals include biocides, alum and pH adjusting chemicals.

A conventional way of preparing a hydrophobic sizing agent dispersion from these components is to prepare, by mixing and heating in a reactor, a homogenous premixture containing in a suitable ratio water, an active agent, a stabilizer, surfactants and other potential additional chemicals.

After obtaining the homogenous premixture, it is circulated via a high-pressure homogenizer, a colloid mill or a high-revolution centrifugal pump generally several times, until a sufficiently small particle size has been obtained (generally 0.1 - 10 μm). The pressure varies within the range of 50 - 500 bar and the temperature within 50 - 100°C. The dispersion obtained is thereafter run via a heat exchanger into a product container. In the heat exchanger, the temperature of the dispersion is decreased to < 30°C.

Surprisingly, it has now been found that a high-pressure digester, a steam jet digester, primarily designed for cooking starch acts as an extremely good dispersing device in the preparation of a hydrophobic sizing agent dispersion.

The invention will be explained more detailed with refer-

ence to the enclosed drawing. A steam jet digester process acts as follows:

5 A premixture is prepared in a reactor 1 according to the same principle as in the afore-mentioned conventional process. After this, the mixture is pumped into a digester portion 2 itself, wherein the mixture contacts a high-pressure steam flow 3 and the temperature and the pressure increase (the pressure generally to 2 - 15 bar and
10 the temperature to 100 - 200°C). The dispersion formed is thereafter run into a tubular reactor 4, after which the pressure and the temperature are decreased in an expander device 5 and the excess of steam may be separated by means of a steam condenser 6. The homogenous product
15 formed is then run via a heat exchanger into a product container.

This process deviates from a conventional process as follows:

20

Conventional process:

Pressure 50 - 500 bar
Temperature 50 - 100°C

25

Steam jet digester process

Pressure 2 - 15 bar
Temperature 100 - 200°C

30

The preparation of a hydrophobic sizing agent dispersion in a process of a steam jet digester type makes it possible to use high solids contents during the processing, and since the delay in the digester and reactor tubes is
35 extremely short, usually < 2 minutes, this makes it possible to use very small units having a large production capacity.

Example 1

In a laboratory scale a stearine/palmitine alkyl ketene dimer (AKD) premixture was prepared having the following composition:

water	800 g
AKD	200 g
Orotan SN*	3.0 g
10 Raisamyl 150E**	22 g

* Naphthalene formaldehyde sulphonate condensate, sodium salt

** Cationic potato starch (DS = 0.05).

15 The starch was cooked before adding.

This premixture was divided into two portions, one of which was run 3 times through the laboratory high-pressure homogenizer (Rannie). The pressure was 200 bar, the temperature 70°C. The other portion was run once through a laboratory-scale steam-jet digester, the temperature being 120°C and the pressure 3 bar. Both emulsions were diluted into a solids content of 12,5% and cooled into room temperature.

25

The following characteristics were measured from each of the dispersions: viscosity (Brookfield) and average particle size.

30 High-pressure homogenizer/Steam-jet digester

Viscosity	10 cP	8 cP
-----------	-------	------

Average particle size	0.56 μm	0.60 μm
-----------------------	--------------------	--------------------

35

The results show that the dispersions are by their characteristics nearly identical.

The dispersions were kept at room temperature for one month, and the same measurements were performed again, whereby the result was as follows:

5

High-pressure homogenizer/Steam-jet digester

	Viscosity	15 cP	16 cP
10	Average particle size	0.86 μm	0.95 μm

The results show that the storage stabilities of the two dispersions are of the same order.

15 **Example 2**

In a laboratory scale an alkenyl succinic-acid anhydride* (ASA) premixture was prepared having the following composition:

20

water	900 g
ASA	50 g
Orotan SN	0.5 g
Raisamyl 150E	100 g

25

* As an alkenyl succinic-acid anhydride anhydrides derived from straight-chain C_{13} - C_{20} α -olefines were used.

30 This premixture was divided into two portions as well, one of which was run through a high-pressure homogenizer (pressure 200 bar, temperature 50°C) and the other portion was run through a steam-jet digester, the temperature being 110°C and the pressure 1.5 bar.

35 The dispersions produced were diluted into a solids content of 7.5%, and their viscosity and average particle size were measured.

High-pressure homogenizer/Steam-jet digester

Viscosity 600 cP 520 cP

5

Average particle size 0.50 μm 0.65 μm

The results show that the dispersions are nearly identical.

10

A value $< 1 \mu\text{m}$ is regarded as a generally accepted particle size in products of this type.

Claims

1. A method for preparing a hydrophobic sizing agent especially for a paper making process, wherein basic sizing agent components based on an alkenyl-succinic-acid anhydride (ASA), an alkyl ketene dimer (AKD) or a resin and from additives preferably added thereto a sizing agent premixture is prepared by heating and mixing and this premixture is subjected to a pressurized thermal and mechanical treatment for obtaining a sizing agent dispersion, **characterized** in that the pressurized treatment is performed at a pressure of 2 - 15 bar and at a temperature of 100 - 200°C during a period of less than 2 minutes.
2. A method according to Claim 1, **characterized** in that the pressurized treatment is performed by subjecting the sizing agent premixture to a high-pressure water steam directed at a high speed.

